Coexistence of scale invariant states in a scale free system

Evan Hohlfeld*
Department of Physics, University of Massachusetts, Amherst, MA 01003, USA

Soft solids, such as elastomers, have an instability toward the nucleation and growth of sharply creased surface folds. We develop an analogy between this instability and a first order phase transition by constructing an isolated fold as a domain wall-like structure separating two, coexisting scale invariant deformations of an incompressible elastomer: an affine deformation, and a crease. We relate the existence of this surface folding instability and the striking non-existence of a phase boundary separating the two scale invariant deformations to certain convexity properties of the elastomer free energy.

arXiv:1302.6152v1 [cond-mat.soft] 25 Feb 2013

Liquefaction of argon, nematic ordering of the liquid crystal 5CB, and allotropy in iron are well studied examples of first order phase transitions in materials. These phenomena can be understood at a macroscopic scale as coexistences between different scale free, homogenous states—phases. Recently, soft solids such as a hydrogels, elastomers, and tissues, were discovered to possess a novel kind of scale free instability with an uncanny, though imperfect resemblance to a first order phase transition [1–3]. When a soft solid surface is sufficiently compressed, infinitesimal, sharply creased folds can nucleate and grow [1, 3]. This critical compression is independent of the sample shape and marks the coexistence of localized folds, called *sulci*, and a smooth free surface. With further quasi-static compression, work flows in from the displaced boundaries of the sample to the individual sulci as these grow. During growth, the compression close to each sulcus remains at the coexistence value [2]. The amount of work is proportional to the folded *volume*, and hence can be interpreted as the work of transformation. Beyond a second, larger critical compression the flat free surface loses metastability and sulci spontaneously form [1, 4]. This second critical compression can be understood as a kind of spinodal point for the flat surface [2, 5]. The analogy with a phase transition fails, however, when we attempt identify a sulcus with a "droplet" of a new phase, since, for example, no clear phase boundary divides the sulcus from the surrounding elastomer [2]. In this Letter we propose an explanation for the partial analogy between the sulcification (or creasing) instability of an elastomer surface and a phase transition. Whereas phase transitions are transformations between distinct *homogenous*, scale invariant states, instabilities like sulcification occur when a system transitions between scale invariant, though potentially *inhomogeneous* states. We explain how to construct these states, the transitions between them, and the striking absence of phase boundaries.

Recent interest in sulcification has focused on the effects of swelling [6–9], growth [10–12], applied fields [13], mechanical confinement[1, 14–18], and imperfections [19], on how patterns form[2, 3, 20], and on connections to other phenomena such as plastic folding [21]. In previous work we calculated the critical strain for sulcificiation [1] and developed a bifurcation and pattern formation theory based on treating sulcification point as novel kind of nonlinear critical point [2]. The later work was built on the supposition that an isolated sulcus in a critically compressed rubber half-space is a local minimum of energy up to translations and changes of scale. At the critical point, the scaling mode changes stability, allowing a nucleated sulcus to grow from infinitesimal size. Linearization fails to detect this instability because scaling changes the size of the sulcus without changing the magnitude of its deformation gradient.

The possibility of such an undetectable small amplitude instability involving a continuous deformation was actually first anticipated by Weierstrass when he distinguished so-called weak (i.e. merely linearly stable) local minima from strong local minima. The detection of Weierstrass instabilities has remained an open problem, however [22]. Our exposition here adds to these ongoing discussions by showing how to construct an isolated sulcus solution in a simple elastomer, and how this construction might generalize to more complex systems.

Our plan is to systematically develop the analogy between sulcification and a phase transition. To frame this discussion, we consider a sample of incompressible neo-Hookean elastomer. This is a model material for many rubbery solids which are dramatically softer in simple shear than in volumetric compression. It is compactly specified by the Lagrangian density

$$\mathcal{L}\left(\mathbf{A}\right) = \frac{\mu}{2} A^i_\alpha A^\alpha_i - p\left(\det[A^i_\alpha] - 1\right) \tag{1}$$

where the matrix $\mathbf{A} = \partial\mathbf{x}/\partial\mathbf{X}$ is the gradient of the deformation $\mathbf{x}(\mathbf{X})$ of a reference volume. The first term in (1) governs the entropic elasticity of the network chains with shear modulus μ, and the second term, involving the Lagrange multiplier p, enforces the nonlinear incompressibility constraint $\det \partial\mathbf{x}/\partial\mathbf{X} = 1$. When restricted to isochoric deformations so that the constraint term in (1) is identically zero, $\mathcal{L} = \mathcal{F}$, the free energy density of the elastomer. In terms of $\mathcal{F}$, we impose the volumetric constraint by setting $\mathcal{F}(\mathbf{A}) = +\infty$ for $\det(\mathbf{A}) \neq 1$.

The Lagrangian density $\mathcal{L}$ is invariant under rigid translations and rotations of $\mathbf{x}$ and $\mathbf{X}$, separately, i.e.

$\mathbf{x} \to \mathcal{O}\mathbf{x} + \mathbf{c}$ or $\mathbf{X} \to \mathcal{O}\mathbf{X} + \mathbf{c}$ where $\mathcal{O}$ is an orthogonal matrix and $\mathbf{c}$ is a vector. The first of these symmetries is the so-called objectivity of the model while the second expresses that the elastomer is a homogenous and isotropic material. Our focus is on another symmetry of $\mathcal{L}$. Because the Lagrangian density $\mathcal{L}$ is a function of the dimensionless deformation gradient $\mathbf{A}$, it is also invariant under the scale transformation $\{\mathbf{x}, \mathbf{X}\} \to \{L\mathbf{x}, L\mathbf{X}\}$ for any scaling factor $L > 0$. Unlike rigid translations and rotations, however, the measure $d\mathbf{X}$ is not invariant under scale transformations. Thus while a scale transformation is not a symmetry of the Lagrangian $L = \int_\Omega \mathcal{L} d\mathbf{X}$—and so not associated with a Noetherian conservation law—it is nevertheless a symmetry of the Euler-Lagrange equation.

Many material models possess scale symmetry as an intermediate asymptotic property between the molecular length scale and the system scale. The configurations of small enough patches of material, which are still larger than the small-scale cut-off, must be independent of both the macroscopic and microscopic details. In particular such configurations must become invariant under rescaling as the system size is taken to infinity.

To compare the elastomer with other materials, it is helpful to view the deformation gradient $\mathbf{A}$ as a tensor order parameter. Then, what distinguishes the elastomer from other materials with tensor order parameters, say nematic liquid crystals, is the *compatibility constraint* that $\mathbf{A} = \partial\mathbf{x}/\partial\mathbf{X}$. A similar constraint holds for the scalar phase variables that appear in theories of smectic liquid crystals and superconductors. What distinguishes the elastomer from smectics and superconductors is the vector nature of the "phase" variable $\mathbf{x}$. Because of the compatibility constraint, an external field conjugate to $\mathbf{A}$ is equivalent to the application of tractions to the boundary of a sample. The compatibility constraint plays a fundamental role in our analysis below.

Even though rubbers are stable enough materials to use in car tires, let us for the moment forget this stability and compute the "phase diagram" corresponding to (1), viewed as an abstract material. For simplicity, we consider only plane strain deformations so that $\mathbf{x}, \mathbf{X} \in \mathbb{R}^2$. In this exercise, we would identify different phases with homogenous values of $\mathbf{A}$ corresponding to distinct local minima of the free energy density $\mathcal{F}$. This is, for example, how the austenite and martensite phases of shape-memory alloys are described. If $\mathcal{F}$ has multiple local minima, then we can consider the coexistence of any two phases. Because of the compatibility constraint, phase boundaries between such phases can involve at most a rank-one jump in $\mathbf{A}$. That is if $\mathbf{A}_1$ and $\mathbf{A}_2$ are the two phases then $\mathbf{A}_1 - \mathbf{A}_2 = \mathbf{a} \otimes \mathbf{N}$ where $\mathbf{N}$ is the interface normal and $\mathbf{a}$ is some vector. (Otherwise the elastomer material would tear along the phase boundary.) One can check that $\mathcal{F}$ is rank-one convex[28]. Invoking Maxwell's famous argument, we conclude that no two phases can coexist for any value of applied field (i.e. imposed stress). Hence the neo-Hookean material has no phase transitions.

Since Maxwell's argument is based on convexity, it is perhaps troubling that the neo-Hookean free energy density is not actually convex in $\mathbf{A}$. This is easy to see if one imagines rotating a homogeneous volume by 180° so that $\mathbf{A} \to -\mathbf{A}$. The chord joining these states passes though $\mathbf{A} = \mathbf{0}$, which is a point of infinite energy because of the isochoric constraint. To see the consequence of this non-convexity of $\mathcal{L}$, we reframe our exercise to examine an infinite elastomer-vacuum interface. We are now looking for interfacial phase transitions.

First let us fix a Cartesian coordinate systems (X^1, X^2) in the material frame and (x^1, x^2) in the laboratory frame so that the elastomer occupies the material space $X^2 < 0$. We can freely assume the deformation $\mathbf{x}(\mathbf{0}) = \mathbf{0}$ so that the deformed elastomer also occupies and laboratory space $x^2 < 0$. Because of the free boundary condition on $X^2 = 0$ we must have $\mathbf{A} = \mathrm{diag}(\lambda, 1/\lambda)$, where $1 - \lambda$ is the lateral compression of the elastomer interface. We can check the stability of the interface by computing the speeds of shear and Rayleigh waves, which must be real in a stable material. The shear wave speed is always real (because of rank-one convexity), but the Rayleigh wave speed is imaginary for compressions exceeding $1 - \lambda_B \approx 0.45$ [4]. This surface instability is known as Biot's instability. Note that if the free energy density $\mathcal{F}$ were convex, Biot's instability would not exist.

In many materials, the vanishing of a wave speed indicates a phase transition. For instance, the speed of sound vanishes at the liquid-vapor critical point. In our present model, the shear wave speed vanishes as $\mu \to 0$, and the $\mu = 0$ limit of Lagrangian density (1) describes a perfect, incompressible fluid.

Let's, then, conduct the following thought experiment. Suppose a thermal fluctuation (or other perturbation) triggers Biot's instability. Recent post-buckling analysis of Biot's instability has shown that Biot's instability is sub-critical, which suggests the hypothetical surface phase transition is first order [23]. Like most first order phase transitions, we expect that the fluctuation nucleates an initially localized, growing "bubble" of some highly deformed configuration. Because the neo-Hookean material has no bulk phase transitions, we might guess that the emerging phase in this bubble involves some kind of frozen surface wave or roughness. If the amplitude of this roughness were finite, we could use the scale symmetry of $\mathcal{L}$ to rescale the amplitude to zero and recover the initial, flat interface at large scales. But as the flat interface is unstable, it must be that the alternative phase has infinite amplitude fluctuations.

The signature of such a fluctuation-dominated state in a finite size system would be the non-attainment of the energy minimum. That is, a minimizing sequence of deformations starting from a super critically compressed




FIG. 1: A sulcus in a unit-diamater half-disc compressed to a width λ (blowups on right) is mapped to a domain wall in a strip (representative configurations $A-C$) by conformal change of variable and coordinates [double headed arrow, also Eqs. (3)]. Color (blue to red) indicates a linear blow-up of pressure as $s \to -\infty$. The size of the sulcus L is dual to the position of the domain wall on the s-axis in the strip. The bifurcation diagram (blue line) relates $L^2 \propto \lambda - \lambda^*$ as was explained in [2]; the critical compression $1 - \lambda^* \approx 0.35$

flat interface would develop wilder and wilder surface undulations at finer and finer scales. A precise criterion for the non-attainment of an energy minimum was given by C. B. Morrey who proved that so-called quasiconvex energy densities always attain their energy minimum [24][29]. The free energy density $\mathcal{F}$ satisfies a stronger condition called polyconvexity [25][30], so its form rules out any roughening of the interface.

Because of the quasiconvex form of $\mathcal{F}$, at long times, any finite volume of elastomer surrounding the initial disturbance must settle into a new equilibrium, which in an infinite system must be scale invariant. So we now propose to identify all deformations which are invariant under scale transformation.

Scale invariant deformations are most easily identified by picking an origin and changing to logarithmic-polar coordinates (which is a conformal coordinate transformation from the standard Cartesian coordinates on $\mathbb{R}^2$). We define new coordinates systems (T, Θ) and (s, ϕ) by the relations

$$X^1 = \cos(\Theta)e^T \qquad X^2 = \sin(\Theta)e^T \tag{2}$$

$$x^1 = \cos(\phi)e^s \qquad x^2 = \sin(\phi)e^s. \tag{3}$$

(I.e. $T = \log R$, the radial coordinate in the reference body, and likewise for s.) This coordinate transformation maps an annulus in the the Cartesian coordinates to a finite strip in the logarithmic-polar coordinates as illustrated in Fig. 1. In particular, the $X^2 < 0$ half-plane is mapped to the infinite strip $(T, \Theta) \in [-\infty, \infty] \times [-\frac{\pi}{2}, \frac{\pi}{2}]$. More importantly, this coordinate transformation maps rescaling in the Cartesian coordinates to simultaneous translation in s and T. The coordinate transformation also maps power-law type singularities in the deformation gradient to T-translation invariant deformation gradients on the infinite strip.

In the original Cartesian coordinates, the Euler-Lagrange equation for (1) is $\partial S_i^\alpha / \partial X^\alpha = 0$, where the nominal stress $S_i^\alpha = \partial \mathcal{L} / \partial A_\alpha^i$. The divergence form of this equations is direct consequence of the compatibility constraint on $\mathbf{A}$. In the new coordinates, the equations of equilibrium take the form (in units where $\mu = 1$)

$$-\left(\frac{\partial^2 s}{\partial T^2} + \frac{\partial^2 s}{\partial \Theta^2}\right) + \left(\frac{\partial \phi}{\partial T}\right)^2 + \left(\frac{\partial \phi}{\partial \Theta}\right)^2 - \left(\frac{\partial s}{\partial T}\right)^2 - \left(\frac{\partial s}{\partial \Theta}\right)^2 - \frac{\partial p}{\partial T}\frac{\partial \phi}{\partial \Theta} + \frac{\partial p}{\partial \Theta}\frac{\partial \phi}{\partial T} = 0 \tag{4}$$

$$-\left(\frac{\partial^2 \phi}{\partial T^2} + \frac{\partial^2 \phi}{\partial \Theta^2}\right) + 2\left(\frac{\partial \phi}{\partial T}\frac{\partial s}{\partial T} + \frac{\partial \phi}{\partial \Theta}\frac{\partial s}{\partial \Theta}\right) + \frac{\partial p}{\partial T}\frac{\partial s}{\partial \Theta} - \frac{\partial p}{\partial \Theta}\frac{\partial s}{\partial T} = 0, \tag{5}$$

the isochoric constraint becomes

$$\frac{\partial s}{\partial T}\frac{\partial \phi}{\partial \Theta} - \frac{\partial s}{\partial \Theta}\frac{\partial \phi}{\partial T} = e^{2(T-s)}, \tag{6}$$

and boundary conditions on the surfaces $\Theta = \pm\frac{\pi}{2}$ (i.e. the erstwhile free surface $X^2 = 0$) are

$$\frac{\partial s}{\partial \Theta} - p\frac{\partial \phi}{\partial T} = 0, \quad \frac{\partial \phi}{\partial \Theta} + p\frac{\partial s}{\partial T} = 0. \tag{7}$$

Scale invariant deformations, that is T-homogenous solutions to Eqs. (5-7), can be parametrized as $\partial s/\partial \Theta = f(\Theta)$, $\partial \phi/\partial \Theta = g(\Theta)$, $\partial s/\partial T = 1$, and $\partial \phi/\partial T = 0$. Inspection of Eqs. (5-7) shows that such a form requires $p = CT + h(\Theta)$. Solutions with $C = 0$ correspond to affine deformations. In the logarithmic-polar coordinates these are $s = T + \frac{1}{2}\log\left(\lambda^2 \sin^2\Theta + \frac{1}{\lambda^2}\cos^2\Theta\right)$, $\lambda^2 \tan\phi = \tan\Theta$. Solutions with $C \neq 0$ correspond to creased deformations with different opening angles β and with different amounts of shear applied to the boundaries $\Theta = \pm\pi/2$. All of these deformations develop infinite compressive stresses normal to these boundaries as

$T \to -\infty$, which would violate the second of Eqs. (7) unless $\beta = 0$ so that the crease closes to self-contact. The only solution with $\beta = 0$ and no surface shear is $s = T - \frac{1}{2}\log 2$, $\phi = 2\Theta$, $C = \frac{3}{2}$, and $h = const.$[26]. Note that the creased deformation spontaneously breaks the x^1-translation symmetry of the interface.

The creased ($C \neq 0$) deformation and affine ($C = 0$) deformations are all linearly stable, but for different reasons. The affine deformations are linearly stable (for $\lambda > \lambda_B$) because the local curvature of the free energy density function provides a restoring force for small deformations. The crease is stable because it generates its own confining pressure. Formally, this existence of this pressure can be traced the terms in Eqs. (5) which are quadratic in s and ϕ and to the incompressibility constraint. These terms arise in the change of variable to logarithmic-polar coordinates because of the tensor character of the nominal stress $S_i^\alpha = \partial\mathcal{L}/\partial A_\alpha^i$, and the divergence form of the Euler-Lagrange equation $\partial S_i^\alpha/\partial X^\alpha$. Thus the same features of the elastomer that yielded the non-convexity of $\mathcal{F}$ (incompressibility) and the stability of the homogenous phase in spite of this non-convexity (the compatibility constraint) also stabilize the inhomogeneous scale invariant deformation (i.e. the crease). The crease and the affine deformations are distinct manifolds of linearly stable, T-translation invariant configurations. So just as for two distinct stable phases, there must be a domain wall type solution which interpolates from the creased manifold at $T = -\infty$ to the affine manifold at $T = +\infty$.

Coexistence between the two scale invariant states occurs when the domain wall can freely traverse the strip, see Fig. 1. Transforming this mobile domain wall back to Cartesian coordinates yields the sulcus deformation of the critically compressed half-space. The location of the domain wall in the strip gives the size of the sulcus in the half-space, hence the mobility of the domain wall is equivalent to the soft growth mode of a sulcus in a critically strained half-space. While the width of most domain walls is set by microscopic physics, the rank-one convexity of $\mathcal{F}$ precludes the formation of sharp phase boundary. Hence the width of our domain wall must be fixed by the width of the strip. The domain wall turns out to have an exponential profile, which translates to power law tail of the sulcus in the Cartesian coordinates and gives rise to the energy of transformation [2].

Practically, we find the domain wall solution by solving Eqs. (5-7) numerically using finite element and continuation methods as in Ref. [1]. We impose the creased and affine deformations as boundary conditions on opposite ends of a long strip in the $T-\Theta$ plane. The two imposed deformations can have a relative shift in the x^2 direction. The value of this shift, which is the depth of the crease within the sulcus, is fixed (relative to the size of the sulcus) by requiring that the integral of the traction in the x^2 direction vanishes on either constrained surface. We find coexistence between the crease and an affine deformation at the critical compression of $1-\lambda^* \approx 0.35$, which is similar to what has been reported elsewhere [1, 15].

The principle implied our discussion of the incompressible neo-Hookean model is that while ordinary phase stability follows from rank-one convexity of the free energy, this property is not strong enough to preclude all processes which resemble phase transitions. In general, scale free material models can have multiple scale invariant potential wells, and some of these may correspond to *inhomogeneous* states. However, a local analysis of the free energy density will only detect the homogenous states, i.e. phases. Rather, one should look for all scale invariant configurations, whether or not these are homogenous. Whenever a model has multiple scale invariant potential wells, whether or not they correspond to distinct phases, there are associated coexistence conditions between every pair. When coexistence occurs, the mode in which one state transforms into the other (i.e. the growth mode) is an emergent soft mode of the whole system which can dramatically change its response to external stimuli. It is interesting to note that our construction doesn't directly use the free energy density $\mathcal{F}$, so it makes sense even for systems which are out of equilibrium. We also remark that integrability of the strain energy density close to the origin $\mathbf{X} = \mathbf{0}$ implies the coordinate-transformed deformation gradient must in any case be bounded as $T \to -\infty$. So a potential alternative to a T-translation homogenous state, such as a crease, is a T-periodic state. Such configurations might be relevant in the finely twinned microstructure that sometimes forms during a martensitic phase transition. Our method of constructing a sulcus potentially has an immediate application in liquid crystal elastomers. A recent experiment suggests that sulcification or creasing in these materials may induce topological changes in the nematic director field [27]. The existence of a director field in these materials potentially enriches the space of inhomogeneous, scale invariant deformations beyond the crease studied here.

* Electronic address: evanhohlfeld@gmail.com

[1] E. Hohlfeld and L. Mahadevan, Phys. Rev. Lett. **106**, 105702 (2011).

[2] E. Hohlfeld and L. Mahadevan, Phys. Rev. Lett. **109**, 025701 (2012).

[3] D. Chen, S. Cai, Z. Suo, and R. C. Hayward, Phys. Rev. Lett. **109**, 038001 (2012).

[4] M. A. Biot. *Mechanics of Incremental Deformations* (John Wiley and Sons, New York, 1965).

[5] A. Onuki, Phys. Rev. A **39**, 5932–5948 (1989).

[6] T. Tanaka et. al. in *Molecular Conformation and Dynamics of Macromolecules in Condensed Systems*, edited by M. Nagasawa (Elsevier, New York, 1988).

[7] V. Trujillo, J. Kim, and R. C. Hayward, Soft Matter **4**,

564–569 (2008).
[8] J. Kim and J. Yoon and R. C. Hayward, Nature Materials **9**,159-164 (2010).
[9] N. Zalachas, S. Cai, Z. Suo, Y. Lapusta, Int. J. Solids and Struc. **50**, 920–927 (2013).
[10] P. V. Baly, R. J. Okamoto, G. Xu, Y. Shi, and L. A. Taber, Phys. Biol. **10**, 016005 (2013).
[11] L. Jin, S. Cai and Z. Suo, Euro. Phys. Lett. **95**, 64002 (2011).
[12] J. Dervaux, Y. Couder and M. A. Guedeau-Boudeville and M. Ben Amar, Phys. Rev. Lett. **107**, 018103 (2011).
[13] Q. Wang, L. Zhang, and X. Zhao, Phys. Rev. Lett. **106**, 118301 (2011).
[14] S. Mora, M. Abkarian, H. Tabuteau, and Y. Pomeau, Soft Matter **7**, 10612-10619 (2011).
[15] W. Hong, X. Zhao, Z. Suo, Appl. Phys. Lett. **95**, 111901 (2009).
[16] A. N. Gent and I. S. Cho, Surface instabilitiesin compressed or bent rubber blocks. Rubber Chem. and Tech. **72**, 253–262 (1999).
[17] A. Ghatak and A. L. Das, Phys. Rev. Lett. **99**, 076101 (2007).
[18] P. M. Reis, F. Corson, A. Boudaoud, and B. Roman, Phys. Rev. Lett., **103**, 045501 (2009)
[19] Y. Cao and J. W. Hutchinson, Proc. R. Soc. A **468**, 94-115 (2011).
[20] T. Tallinen, J. S. Biggins, and L. Mahadevan, Phys. Rev. Lett. **110**, 024302 (2013).
[21] N. K. Sundaram, Y. Guo, and S. Chandrasekar, Phys. Rev. Lett **109**, 106001 (2012).
[22] J. M. Ball and J. E. Marsden, Arch. Rat. Mech. Anal. **86**, 251–277 (1984). Y. Grabovsky and T. Mengsha, Trans. Amer. Math. Soc. **361**, 1495–1541 (2009).
[23] J. Hutchinson, Phil. Trans. R. Soc. A, (2013)
[24] C. B. Morrey, Jr., Pacific J. Math. **2**, 25-53 (1952). E. Acerbi and N. Fusco, Arch. Rat. Mech. Anal. **21**, 152–145 (1984).
[25] J. M. Ball, Arch. Rat. Mech. Anal. **63**, 337–403 (1977).
[26] S. A. Silling, J. App. Mech. **58**, 70–74 (1991).
[27] M. F. Islam, M. Nobili, F. Ye, T. C. Lubensky, and A. G. Yodh, Phys. Rev. Lett **95**, 148301 (2005).
[28] A function F is rank-one convex if $F(\mathbf{A} + (1-t)\mathbf{a} \otimes \mathbf{b}) \leq tF(\mathbf{A}) + (1-t)F(\mathbf{A} + \mathbf{a} \otimes \mathbf{b})$ for every number $t \in [0,1]$, matrix $\mathbf{A}$, and pair of vectors $\mathbf{a}$, $\mathbf{b}$. In our case this condition is equivalent to the Lagrange-Hadamard inequality, or a finite shear wave speed at all states of deformation.
[29] A function F is quasiconvex if $\int_Q F(\mathbf{A} + \mathbf{B}(\mathbf{X}))dV \geq F(\mathbf{A})\text{vol}(Q)$ where Q is the unit cube in $\mathbb{R}^d$, for every matrix $\mathbf{A}$ and *function* $\mathbf{B}$ which is the gradient of a Q-periodic function. Quasiconvexity can be compared to Jensen's inequality, which automatically holds for convex functions.
[30] A function F is polyconvex if it is a convex function of null Lagrangians. For example if $F(\mathbf{A}, b)$ is a jointly convex function of the matrix $\mathbf{A}$ and number b, then $F(\mathbf{A}, \det \mathbf{A})$ is polyconvex.